

Analysis for the aptitude for food contact / BFR XXXVI

AIRTEX GRAPHITE - N01 MP 3037501 SORTE: 55DC-GRA-N01
GRAMMAGE: 55G/M² N°DE FABRICATION: 1635J08401



According to the analysis carried out in laboratory:

Heavy metals in packaging and paper - ENV 12497 / ENV 12498 - materials in contact with food
PCP - GC/MS - ISO 15320 – For paper
PCB - EN ISO 15318 - J6545
Glyoxal in paper (J6528) - Photometry - DIN 54603
Fluoride – NF T 90-004
Organoleptic Inertia on paper - NF EN 1230-2
Formaldehyde on paper - NF EN 1541
Search for antimicrobial agents - EN 1104 - EUROFINS FOR PAPER
Optical whitener - EN 648 - materials in contact with food
Colours fastness in water - bleeding evaluation - EN 646:2006-08
Azo-dyes (natural fibrous material) - EN 14362-1: 2003 + DIN EN 14362-1: 2012
Primary aromatic amines in paper
Monochloro-1,2-propandiol (MCPD) and 1,3-Dichloro-2-propanol (DCP)
Thiazolinones - LC-MS/MS
Anthraquinone pesticide - GC-MSD

The results of the tested product are conform to the recommendation of BfR (Federal Institute for Risk Assessment) XXXVI, for the aptitude to food contact.

Eurofins ATS - 505 rue Louis Berton - CS 50550
13594 Aix-en-Provence Cedex 3 - France
Tel : +33 4.42.39.78.08

www.eurofins.com / ats@eurofins.com